Vishay Dale Thin Film

QPL MIL-PRF-55342 Qualified Thin Film Resistor, Surface Mount Chip




Thin Film Mil chip resistors feature all sputtered wraparound termination for excellent adhesion and dimensional uniformity. They are ideal in applications requiring stringent performance requirements. Established reliability is assured through 100 % screening and extensive environmental lot testing. Wafer is sawed producing exact dimensions and clean, straight edges.

Note

 Specification changed by D.S.C.C. from MIL-R-55342 to MIL-PRF-55342

CONSTRUCTION



FEATURES



- Established reliability, "R" failure rate level (100 ppm), C = 2
- High purity alumina substrate 99.6 % purity
- Wraparound termination featuring a tenacious adhesion layer covered with an electroplated nickel barrier layer for + 150 °C operating conditions
- Very low noise and voltage coefficient (< - 25 dB, 0.5 ppm/V)
- Non-inductive
- Laser-trimmed tolerances ± 0.1 %
- Wraparound resistance less than 0.010 Ω typical
- In-lot tracking less than 5 ppm/°C
- Complete MIL-testing available in-house
- Antistatic waffle pack or tape and reel packaging available
- Military/aerospace/QPL

Note

** Please see document "Vishay Material Category Policy": www.vishav.com/doc?99902

TYPICAL PERFORMANCE

		ABSOLUTE
	TCR	25
	TOL.	0.1

STANDARD ELECTRICAL SPECIFICATIONS				
TEST	SPECIFICATIONS	CONDITIONS		
Material	Passivated nichrome	-		
Resistance Range	10 Ω to 6.19 MΩ	-		
TCR: Absolute	± 25 ppm/°C to ± 300 ppm/°C	- 55 °C to + 125 °C		
Tolerance: Absolute	± 0.1 % to ± 10 %	+ 25 °C		
Stability: Absolute	ΔR ± 0.02 %	2000 h at + 70 °C		
Stability: Ratio	-	-		
Voltage Coefficient	0.1 ppm/V	-		
Working Voltage	30 V to 200 V	-		
Operating Temperature Range	- 55 °C to + 125 °C	-		
Storage Temperature Range	- 55 °C to + 150 °C	-		
Noise	< - 25 dB	-		
Shelf Life Stability: Absolute	$\Delta R \pm 0.01 \%$	1 year at + 25 °C		

COMPONENT RATINGS							
CASE SIZE	POWER RATING (mW)	WORKING	RESISTANCE RANGE (Ω) BY CHARACTERISTICS TOLERANCE				
		VOLTAGE (V)	E (0.1 %)	E (1 %, 2 %, 5 %)	H, K, M (0.1 %)	H, K, M (1 %, 2 %, 5 %)	
M55342/01	50	40	49.9 to 150K	49.9 to 150K	20 to 150K	20 to 150K	
M55342/02	125	40	49.9 to 301K	49.9 to 301K	20 to 301K	20 to 301K	
M55342/03	200	75	49.9 to 649K	49.9 to 649K	10 to 649K	10 to 649K	
M55342/04	150	125	49.9 to 1.69M	49.9 to 1.69M	10 to 1.69M	10 to 1.69M	
M55342/05	225	175	49.9 to 3.16M	49.9 to 3.16M	10 to 3.16M	10 to 3.16M	
M55342/06	150	50	49.9 to 475K	49.9 to 475K	10 to 475K	10 to 475K	
D55342/07	250	100	49.9 to 1.5M	49.9 to 1.5M	10 to 1.5M	10 to 1.5M	
M55342/08	800	150	49.9 to 4.02M	49.9 to 4.02M	10 to 4.02M	10 to 4.02M	
M55342/09	1000	200	49.9 to 6.19M	49.9 to 6.19M	10 to 6.19M	10 to 6.19M	
M55342/10	500	75	49.9 to 1M	49.9 to 1M	49.9 to 1M	49.9 to 1M	
M55342/11	50	30	49.9 to 100K	49.9 to 100K	20 to 100K	20 to 100K	
M55342/12	100	50	49.9 to 258K	49.9 to 261K	10 to 258K	10 to 261K	


Note

• Values listed are a guide, refer to MIL spec for value/tolerance allowance



Vishay Dale Thin Film

DIMENSIONS in inches



CASE SIZE	TERM.	L	W	Т	D	E
M55342/01	В	0.055 ± 0.006	0.025 ± 0.005	0.010 to 0.030	0.010 ± 0.005	0.015 ± 0.005
M55342/02	В	0.055 ± 0.006	0.050 ± 0.005	0.012 to 0.033	0.010 ± 0.005	0.015 ± 0.005
M55342/03	В	0.105 ± 0.007	0.050 ± 0.005	0.015 to 0.033	0.015 ± 0.005	0.015 ± 0.005
M55342/04	В	0.155 ± 0.007	0.050 ± 0.005	0.015 to 0.033	0.015 ± 0.005	0.015 ± 0.005
M55342/05	В	0.230 ± 0.007	0.075 ± 0.005	0.015 to 0.033	0.020 ± 0.005	0.020 ± 0.005
M55342/06	В	0.080 ± 0.006	0.050 ± 0.005	0.015 to 0.033	0.016 ± 0.008	0.015 ± 0.005
D55342/07	В	0.126 ± 0.008	0.063 ± 0.005	0.015 to 0.033	0.020 + 0.005/- 0.010	0.020 + 0.005/- 0.010
M55342/08	В	0.209 + 0.009/- 0.018	0.098 ± 0.005	0.015 to 0.033	0.020 ± 0.005	0.020 ± 0.005
M55342/09	В	0.259 + 0.009/- 0.015	0.124 ± 0.005	0.015 to 0.033	0.020 ± 0.005	0.020 ± 0.005
M55342/10	В	0.105 ± 0.007	0.100 ± 0.005	0.015 to 0.033	0.015 ± 0.005	0.015 ± 0.005
M55342/11	В	0.040 ± 0.005	0.025 ± 0.005	0.010 to 0.030	0.010 ± 0.005	0.015 ± 0.005
M55342/12	В	0.064 ± 0.006	0.032 ± 0.005	0.010 to 0.033	0.012 ± 0.005	0.015 ± 0.005

ENVIRONMENTAL TESTS					
ENVIRONMENTAL TEST	MIL-PRF-55342 LIMITS (ΔR ±)	VISHAY PERFORMANCE (ΔR ±)			
Thermal Shock	0.1 %	0.020 %			
Low Temperature Operation	0.1 %	0.025 %			
Short Time Overload	0.1 %	0.050 %			
High Temperature Exposure	0.1 %	0.009 %			
Resistance to Bonding	0.2 %	0.006 %			
Moisture Resistance	0.2 %	0.004 %			
TCR	± 25 ppm/°C	< 15 ppm/°C			
Life (2000 h at + 70 °C)	0.5 %	0.02 %			
Life (10 000 h at + 70 °C)	2.0 %	0.04 %			


MECHANICAL SPECIFICATIONS			
Resistive Element	Passivated nichrome		
Substrate Material	Alumina		
Chip Terminations	Solder over nickel		
Fused Solder	SN 63		

FSCM CAGE # - 57489



www.vishay.com

Vishay Dale Thin Film



Note

⁽¹⁾ Only add a V at the end of part number to specify Vishay Dale Thin Film for K/M TCR and tolerance 1 % and higher





Vishay

Disclaimer

ALL PRODUCT, PRODUCT SPECIFICATIONS AND DATA ARE SUBJECT TO CHANGE WITHOUT NOTICE TO IMPROVE RELIABILITY, FUNCTION OR DESIGN OR OTHERWISE.

Vishay Intertechnology, Inc., its affiliates, agents, and employees, and all persons acting on its or their behalf (collectively, "Vishay"), disclaim any and all liability for any errors, inaccuracies or incompleteness contained in any datasheet or in any other disclosure relating to any product.

Vishay makes no warranty, representation or guarantee regarding the suitability of the products for any particular purpose or the continuing production of any product. To the maximum extent permitted by applicable law, Vishay disclaims (i) any and all liability arising out of the application or use of any product, (ii) any and all liability, including without limitation special, consequential or incidental damages, and (iii) any and all implied warranties, including warranties of fitness for particular purpose, non-infringement and merchantability.

Statements regarding the suitability of products for certain types of applications are based on Vishay's knowledge of typical requirements that are often placed on Vishay products in generic applications. Such statements are not binding statements about the suitability of products for a particular application. It is the customer's responsibility to validate that a particular product with the properties described in the product specification is suitable for use in a particular application. Parameters provided in datasheets and/or specifications may vary in different applications and performance may vary over time. All operating parameters, including typical parameters, must be validated for each customer application by the customer's technical experts. Product specifications do not expand or otherwise modify Vishay's terms and conditions of purchase, including but not limited to the warranty expressed therein.

Except as expressly indicated in writing, Vishay products are not designed for use in medical, life-saving, or life-sustaining applications or for any other application in which the failure of the Vishay product could result in personal injury or death. Customers using or selling Vishay products not expressly indicated for use in such applications do so at their own risk and agree to fully indemnify and hold Vishay and its distributors harmless from and against any and all claims, liabilities, expenses and damages arising or resulting in connection with such use or sale, including attorneys fees, even if such claim alleges that Vishay or its distributor was negligent regarding the design or manufacture of the part. Please contact authorized Vishay personnel to obtain written terms and conditions regarding products designed for such applications.

No license, express or implied, by estoppel or otherwise, to any intellectual property rights is granted by this document or by any conduct of Vishay. Product names and markings noted herein may be trademarks of their respective owners.

Document Number: 91000 www.vishay.com Revision: 11-Mar-11